



# FLEXICAT GOLD

STYRENE CATALYST

## Product Bulletin

### Description

CRI Catalyst Company ("CRI") Styrene Catalyst **FLEXICAT GOLD** is a non-chromium containing iron oxide catalyst used for the dehydrogenation of ethylbenzene to styrene. In both isothermal and adiabatic commercial operation, **FLEXICAT GOLD** offers the highest activity along with excellent selectivity, low decline rate and excellent mechanical strength. It can also be used in combination to FlexiCat Yellow, FlexiCat Blue or FlexiCat Red for specific performance requirements

### **PACKAGING AND AVAILABILITY**

CRI's styrene catalysts are available in 1500 kg (3306.9 lb) bulk bags.

Normally, the product is available for shipment 12 weeks from receipt of purchase order. Check with your CRI catalyst representative for specific product availability.

### TYPICAL PROPERTIES

Chemical	
Fe <sub>2</sub> O <sub>3</sub> , wt%	Balance
K <sub>2</sub> O, wt%	< 35%
Other Metal Oxides, wt%	< 45%
Physical	
Pellet Shape	Cylinder
Pellet Size – diameter, mm (inches)	3 (1/8)
Apparent Bulk Density, kg/m <sup>3</sup> x 10 <sup>3</sup> (lb/ft <sup>3</sup> )	1.41(88)
Crush Strength, kg/mm (lb/mm)	3.8 (8.3)

### **HEALTH, SAFETY, AND ENVIRONMENTAL PRECAUTIONS**

To ensure safe use of its products, CRI has evaluated the hazards of CRI FLEXICAT GOLD according to the requirements of the OSHA Hazard Communication Standard 29 CFR 1910.1200. Full attention to these hazards and to appropriate health, safety, and precautionary information is essential. Before handling, testing or using this catalyst, a Material Safety Data Sheet must be obtained by contacting a CRI catalyst representative.

### **ADDITIONAL INFORMATION**

All catalyst information supplied by CRI is considered accurate but is furnished with the express understanding that the customer receiving such information shall make its own assessments to determine suitability of such information for customer's particular purpose. All purchases of catalyst from CRI are subject to CRI's standard terms and conditions of sale (including CRI's product warranties) set forth in a sales proposal, sales contract, order acknowledgement, and/or bill of lading.

### **Contact Information**

Houston – Corporate Headquarters  
CRI Catalyst Company  
Two Greenspoint Plaza  
16825 Northchase Dr. Suite 1000  
Houston, Texas 77060-6029  
Tel: (1) 281-874-2600  
Fax: (1) 281-874-2499

United Kingdom  
CRI Catalyst Company U.K. Ltd.  
1650 Parkway  
The Solent Business Park  
Whiteley Fareham, Hampshire  
PO 15-7AH  
United Kingdom  
Tel: (44) 1 489 884 040  
Fax: (44) 1 489 884 049

Singapore  
CRI/Criterion Marketing Asia  
Pacific Pte. Ltd.  
298 Tiong Bahru Road  
#07-03 Central Plaza  
Singapore 168730  
Tel: (65) 6276-3631  
Fax: (65) 6276-7456

[www.cricatalyst.com](http://www.cricatalyst.com)